



Acoustic  
Fire  
Thermal  
Moisture

# Australasian Insulation Supplies Pty Ltd

Industrial & Marine | Commercial & Residential

T +61 (0)8 9417 9494 F +61 (0)8 9417 9595 E sales@ais-group.com.au W www.ais-group.com.au

## PRODUCT DATA SHEET

### Safe'n'Silent™ Pro370

**Type** Plain faced rigid slab

**Material** Stone wool by the ROCKWOOL Group

**Description** Engineered for higher acoustic performance and manufactured with leading edge melt chemistry (+1000°C), fibre orientation and spinning technology to produce a consistent quality stone wool insulation with superior performance.

**Application** High acoustic insulation performance in all partition wall configurations and other noise reductions applications in hospitals, cinemas, schools, offices, residential and industrial buildings.



Properties		Performance	Code or Standard <sup>[1]</sup>				
Thermal	Conductivity (23°C mean)	K value: 0.034 W/m.K					
	Resistance	Thickness (mm)	50	64	75	90	AS/NZS 4859-1
		R-Value (m <sup>2</sup> .K/W)	1.471	1.882	2.205	2.647	
	Specific heat capacity	0.84 kJ/kg.K					
	Aging (8-10 years)	No performance loss					
	Emissivity	0.9 (nominal)				ISO 12241	
Fire	Combustibility	Non-combustible				AS 1530.1	
	Reaction to fire	Euroclass Reaction to Fire classification: A1-Non-Combustible				EN 13501-1	
	Auto ignition temp	Does not occur				ASTM G 72	
	Flash point ignition temp	Does not occur					
	Melting temp	Over 1000°C					
	Linear shrinkage	≤2%				ASTM C 356	
	Calorific value	0.6 MJ/kg (approx) giving a fire load of 1.92 MJ/m <sup>2</sup> at 50mm thickness					
	Fire hazard indices	Ignitability: 0, Spread of flame: 0, Heat evolved: 0, Smoke developed: 0-1				AS/NZS 1530.3	
	Fire growth rate	Does not occur					
	Fire retardant additives	No HBCD (or HBCDD), TCPP or other chemical fire retardant additives					
Mechanical	Compression resistance	≥6.8 kPa at 10% deformation				EN 826	
	Bending radius	900mm at 50mm thickness					
	Coeff thermal expansion	Nil due to the fibrous nature of the material					
	Durability	Shown to have a +50 year service life in all types of exposure					
	Manufactured tolerances	Dimension (Length, Width, Thickness) on request				EN 1602 / 823 / 822	
Chemical	pH value	Aqueous extracts of fibres are neutral or slightly alkaline (pH 7-9) Will not cause or promote corrosion				ASTM C 795 / C 665 AS/NZS 4859-1	
	Chlorides	Approx 10 ppm water leachable chloride and meets nominated standard requirements for use over stainless steel				ASTM C 795 / C 871	
	Compatibility	Compatible with typical industrial and construction materials					
	Biological	Contains no nutrients and will not promote the growth of fungi, moulds or bacteria or attract insects, rodents or vermin					
Moisture	Water repellency	Hydrophobic, highly water resistant				BS 2972 Sect 12	
	Water absorption	Approx 0.5 kg/m <sup>2</sup> (partial immersion)				EN 1609	
	Capillary action	Capillary resisting, will not draw (wick) water up, into or across material					
	Water vapour sorption	From air ≤0.04 (Vol%)				ASTM C1104 / 1104M	
	Vapour resistance	5 MN.s/g (Water vapour diffusion resistance factor (μ) = 1.3)				EN 13469 / 12086	

<b>Sound</b>	<b>Noise absorption</b> [2]	Freq (Hz)	<b>125</b>	<b>250</b>	<b>500</b>	<b>1000</b>	<b>2000</b>	<b>4000</b>	NRC	$\alpha_w$	Class	EN ISO 354 ASTM C 423 EN ISO 11654	
		$\alpha_p$ 50mm	0.20	0.75	1.00	1.00	1.00	1.00	1.00	<b>1.05</b>	<b>1.00</b>		A
		$\alpha_p$ 64mm	0.40	0.90	1.00	1.00	1.00	1.00	1.00	<b>1.10</b>	<b>1.00</b>		A
		$\alpha_p$ 75mm	0.55	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00		1.00
		$\alpha_p$ 90mm	0.70	1.00	1.00	1.00	1.00	1.00	1.00	<b>1.10</b>	<b>1.00</b>		A
<b>Sound insulation</b>	Thickness (mm)	<b>50</b>	<b>64</b>	<b>75</b>	<b>90</b>						INSUL v8 by Marshall Day Acoustics		
	Rw	17	21	25	27	(±3)							
	Rw + Ctr	13	17	22	24	(±3)							
<b>Air flow resistivity</b>	36 x 10 <sup>3</sup> rayl/m (or Pa.s/m <sup>2</sup> , N.s/m <sup>4</sup> )											ISO 9053	
<b>Physical</b>	<b>Dimensions</b>	Length x width 1200 x 600mm											
	<b>Weight per square metre</b>	4 kg/m <sup>2</sup> ±15% at 50mm thickness											
	<b>Non-fibrous (shot) content</b>	Shot size and % weight: 150 µm ≤11% 300 µm ≤1.5% 850 µm ≤0%											ASTM C 1335
<b>Environment</b>	Manufacturing, recycling, use, service life and energy efficiency performance provides a low ecological footprint. No CFC's or HCFC's are used in the manufacturing process												

## Full disclosure

Data in this publication adopts a principle of Full Disclosure – the declaration of relevant property and performance data rather than the selective publication or non-disclosure of data that could limit the capacity to make informed decisions about OH&S risks and other consequences of design and installation decisions. If you require additional data, please ask.

## Technical support

Stone wool is an engineered stone fibre. AIS provides technical support to determine the stone wool material configuration best suited to case specific performance requirements, and the building assembly or industrial system that will optimise ACOUSTIC, FIRE, THERMAL & MOISTURE (AFTM™) design and operational performance.

## Health and safety

Over 60 years of health research concluded that there are no long-term health problems from using stone wool insulation.

Under the World Health Organisation (WHO) and its Monographs Programme of the International Agency for Research on Cancer (IARC) rock (stone) wool is classified as Group 3 (not classifiable as to its carcinogenicity in humans [3]).

It is recommended that for the handling and installation of stone wool the internationally recognised Safety Data Sheet (SDS) be followed (contact AIS or download from the AIS website).

ROCKWOOL International Group stone wool does not contain asbestos.

## Document notices

<b>Version</b>	<b>Original</b>	Original publication: <b>28 March 2017</b>	
<b>Publisher</b>	<b>Australasian Insulation Supplies Pty Ltd</b>	ABN 25 612 643 993	As trustee for AIS Unit Trust
	56 Cutler Road Jandakot WA 6164		© Copyright AIS 2014
	<b>T +61 (0)8 9417 9494</b>	<b>F +61 (0)8 9417 9595</b>	<b>E sales@ais-group.com.au</b>
			<b>W www.ais-group.com.au</b>

[1] When tested to the Code or Standard nominated, the product will provide a performance equal to or better than the performance properties shown.

[2] Tested at 50, 75 and 100mm thicknesses. Sound Absorption Coefficient and Noise Reduction Coefficient values for intermediate stock thicknesses have been calculated by interpolating between tested values.

[3] IARC working group in Man-Made Vitreous Fibres, Volume 81 of the IARC Monographs, Lyon, 9-16 October 2001.

**Disclaimer** This information is for use by suitably qualified industry professionals. Whilst the information presented was to the best of our knowledge accurate and reliable at the time of preparation, no responsibility is accepted for errors and omissions. This information should not be construed as a recommendation to use any product in violation of any patent rights or in breach of any statute or regulation. Industry professionals are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by AIS for any loss or damage caused by any person acting or refraining from action as a result of this information.