

SeaRox SL 660



HC Firebatts 150

Firesafe Insulation

Product description

SeaRox SL 660 is a slab made of stone wool. The product is specially developed to provide maximum fire protection. SeaRox SL 660 can be supplied with reinforced alu foil.

Application

SeaRox SL 660 is used for hydrocarbon fire protection of bulkheads, decks and firewalls.



Product Properties

	Performance			Norm	
	T [°C]	10	100		300
Thermal conductivity	T [°C]	10	100	300	EN 12667
	λ (W/mK)	0,035	0,043	0,073	
Nominal density	150 kg/m ³			EN 1602 / IMO	
Compressive strength	-			EN 826	
Fire classification	Non-combustible Approved for H constructions Low Flame-Spread Properties			Acc. IMO FTP code	
Water absorption (short term)	< 1 kg/m ²			EN 1609 AC	
Max. Application Temperature	Wool: 750°C Facing: 80°C			-	
Sound absorption directly mounted	$\alpha_w = 0,90$ Thickness: 2x50 mm			ISO 354 (approximated) Evaluated after ISO 11 654	
Facings (on request)	Reinforced alu foil			IMO A.653(16) (low flame - spread)	

Dimensions


SeaRox SL 660:

Thickness (mm): 30, 50 mm Length (mm): 1000 mm Width (mm): 600 mm

SeaRox SL 660 ALU:

Thickness (mm): 30, 50 mm Length (mm): 1000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.



Rockwool Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.